

DALLAS LABORATORIES, INC.

Consultants and Technologists
Chemical and Petroleum Chemists

P.O. BOX 152837, DALLAS, TEXAS 75315
1323 WALL ST, DALLAS, TEXAS 75215
PHONE 214/565-0593
FAX 214/565-1094

MEMBERS
AMERICAN CHEMICAL SOCIETY
ASTM INTERNATIONAL
AMERICAN SOCIETY OF MATERIALS

MEMBERS
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Alfatherm Spa – Stab.To di Gorla
A Colombo 275
1-21040 Gorla Minore

Date: August 29, 2018

Attn: Lorenzo Vai

Report No.: 48090-C

24 MONTH PVC WEATHERABILITY REPORT

The PVC profiles listed below have been tested to determine compliance with the weathering requirements of AAMA 307-16. This voluntary specification establishes the minimum requirements for decorative laminate materials intended for application to either the interior or exterior surfaces on AAMA certified profiles. All profiles have been weathered in accordance with ASTM F 964 at New River, Arizona; Miami, Florida; and Medina, Ohio.

Profiles Weathered:

Mandorlo Exterior Laminate

Dates Weathered:

Arizona: 5-16-16 to 5-14-18
Ohio: 6-2-16 to 6-2-18
Florida: 6-7-16 to 6-12-18

MANDORLO EXTERIOR LAMINATE


COLOR CHANGE

	<u>ARIZONA</u>				<u>OHIO</u>				<u>FLORIDA</u>			
	<u>L</u>	<u>a</u>	<u>b</u>	<u>(ΔE)</u>	<u>L</u>	<u>a</u>	<u>b</u>	<u>(ΔE)</u>	<u>L</u>	<u>a</u>	<u>b</u>	<u>(ΔE)</u>
- Initial Value	36.69	9.82	13.69		36.69	9.82	13.69		33.42	8.89	11.33	
- 6 months	32.93	9.47	13.38	(3.77)	34.91	9.67	13.90	(1.78)	33.46	9.80	14.21	(3.02)
- 1 year	33.93	9.56	13.86	(2.76)	34.62	9.26	12.62	(2.38)	33.07	9.87	14.49	(3.33)
- 2 years	32.48	9.62	13.97	(4.20)	34.42	9.56	13.71	(2.27)	34.00	9.07	14.48	(3.21)

RESULTS

The above results indicate compliance with the 24 month weatherability requirements set forth in AAMA 307-16.

DALLAS LABORATORIES, INC.


Kevan W. Jones, Vice President

KWJ/ss